

Raven 430



DESCRIPTION

Raven® 430 (formerly AquataFlex™ F-2) is a two part, 100% solids, solvent-free flexible epoxy coating with moderate chemical resistance. Formulated as a tough, impact resistant coating, it provides improved adhesion and strength over conventional flexible systems.

TYPICAL USES

Surfaces where a tough, flexible coating is required and minor movement and/or traffic impact is expected, including:

- Secondary containment
- Floors
- Troughs
- Pipelines

COLOR

The Part A Resin is white; the Part B Curing Agent is blue. When mixed the product is light blue.

SOLIDS BY VOLUME

100% solids by volume

Volatile Organic Compounds: 0.0 pounds per gallon

FILM THICKNESS

Raven 430 is a 100% solids epoxy with zero shrinkage. Wet film thickness and dry film thickness are the same (i.e. 5 mils WFT = 5 mils DFT). Recommended thickness will vary from 10 - 120 mils based on service conditions.

COVERAGE

Theoretical coverage is 40 square feet per gallon at 40 mils wet film thickness. Actual surface coverage will depend on substrate porosity and roughness. Good painting practices suggest application of two coats for quality assurance. A wet film thickness gauge may be used to determine actual coating coverage.

APPLICATION

Apply with brush, roller, airless or air-assisted spray or other suitable method. Optimal proportioning and mixing is achieved with the use of a Raven Lining Systems approved plural component airless spray system. For best results, apply this product to concrete when its temperature is stable or falling.

THINNING

Do not thin with solvents. If lower viscosity is needed, heat unmixed material by placing the containers in hot tap water until the desired flow properties are obtained. To heat larger quantities, drum heaters or inline heaters on specialized spray

equipment may be used. Unmixed material should not be heated above 150°F.

COMPONENTS AND MIX RATIO

Part A Resin:Part B Curing Agent mix ratio is 1:1 by volume.

HAND MIXING

Individually mix both Part A and Part B containers prior to measuring out 1 part of Part A to 1 part of Part B by volume into a clean disposable pail. Completely mix combined A & B for a minimum of one minute before transferring contents to a clean pail. Continue mixing at least another minute, scraping the sides and bottom, to obtain a thorough mix before application. Properly mixed material will be a uniform color without light or dark spots.

CLEAN UP

To clean tools, use acetone, MEK or xylene. To clean skin, wash immediately and thoroughly with soap and water. Refer to the Material Safety Data Sheet for additional information on health and safety.

POT LIFE

The pot life is 35 minutes for one gallon at 72°F. The working life varies depending on the amount and temperature of epoxy mixed and the ambient temperature.

CURE TIME

Thin film set time varies with substrate temperature and application thickness. Generally, the coating will be tack-free in 10 hours at 72°F and dry-hard in about 22 hours.

RECOAT TIME

This product may be recoated as soon as it becomes tacky but does not transfer to the finger. When applying multiple coats, do not allow more than 24 hours at 72°F substrate temperature to pass between coats, higher temperatures will shorten this window. Before recoating; inspect, clean and dry surface thoroughly to remove all contamination, including amine blush or condensation. If the recoat time is missed, clean and abrade surfaces prior to recoating.

SUBSTRATE TEMPERATURE

Minimum recommended substrate temperature: 40°F

Maximum recommended substrate temperature: 120°F

TEMPERATURE RESISTANCE

Maximum recommended dry temperature: 200°F. Wet temperature resistance depends on chemical concentration and exposure time.

Raven 430

SURFACE PREPARATION

Prior to coating, the substrate must be prepared in a manner that provides a uniform, clean, sound, neutralized surface suitable for the specified coating. The substrate must be free of all contaminants, such as oil, grease, rust, scale or deposits. In general, coating performance is proportional to the degree of surface preparation.

STEEL surfaces may require “Solvent Cleaning” (SSPC-SP 1) to remove oil, grease and other soluble contaminants. Chemical contaminants may be removed according to SSPC-SP 12/NACE No. 5. Identification of the contaminants along with their concentrations may be obtained from laboratory and field tests as described in SSPC-TU 4 “Field Methods for Retrieval and Analysis of Soluble Salts on Substrates”. Surfaces to be coated should then be prepared according to SSPC-SP 5/NACE No.1 “White Blast Cleaning” for immersion service or SSPC-SP 10/NACE No. 2 “Near White Blast Cleaning” for all other service. In certain situations, an alternate procedure may be to use high (>5,000 psi) or ultrahigh (>10,000 psi) pressure water cleaning or water cleaning with sand injection and an approved rust inhibitor. The resulting anchor profile shall be 2.5-5.0 mils and be relative to the coating thickness specified.

CONCRETE AND MASONRY surfaces must be sound and contaminant-free with a surface profile equivalent to a

CSP2 to CSP5 in accordance with ICRI Technical Guideline No. 03732. This can generally be achieved by abrasive blasting, shot blasting, high pressure water cleaning, water jetting, or a combination of methods.

AVAILABLE PACKAGES

Available in one gallon pails (2 gallon kit). Kits are supplied in the correct proportions of A & B; these two components must be mixed together before use. Raven 430 is available through Raven Certified Applicators.

SHELF LIFE AND STORAGE

Product shelf life is 1 year from purchase date in sealed, unmixed containers, stored in a sheltered area between 60°F and 80°F (15°C and 27°C).

SAFETY

Consult the Material Safety Data Sheet for this product concerning health and safety information before using. Strictly follow all notices on the Material Safety Data Sheet and container label. If you do not fully understand the notices and procedures provided on the MSDS or if you cannot strictly comply with them, do not use this product. Actual safety measures are dependent on application methods and work environment. Contact Raven Lining Systems to obtain a copy of the Material Safety Data Sheet at 800-324-2810.

TYPICAL PROPERTIES⁽¹⁾

DESCRIPTION	METHOD	RESULT
Tensile Strength	ASTM D 638	2,400 psi
Tensile Ultimate Elongation	ASTM D 638	170%
Hardness, Shore D	ASTM D 2240	73
Adhesion, Concrete	ASTM D 4541	Substrate Failure

(1) Typical properties are to be considered as representative of current production and should not be construed as specifications.

Warranty and Disclaimer: Raven Lining Systems, Inc. (“Raven”) warrants its products to be free of manufacturing defects in accord with applicable Raven quality control procedures and that they meet the formulation standards of Raven. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. If, within one year from purchase, any product is proven defective, Raven, at its sole option, will either replace the defective product or refund the purchase price. This warranty is void if the product is used contrary to Raven’s written directions.

THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL RAVEN BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. NO ACTION AGAINST RAVEN MAY BE COMMENCED MORE THAN ONE YEAR AFTER THE CLAIM ARISES.